Lemmaco
the golden company

PET silver lamination film

Technical data sheet

Description: Metalized polyester film with chemical treatment. Other side is extrusion coated with low temperature melting resin. This film is suitable for all printed and unprinted papers, cardboard. Excellent resistance to scuff, scratch and tear. Silver look and excellent printability after lamination.

Property	Test methods	Unit	Data	
PHYSICAL DATA				
Total thickness	Internal	µm	22	
MECHANICAL DATA				
Tensile strength	ASTM D882	kg/cm2	MD	-
			TD	-
Broken elongation		%	MD	-
			TD	-
			TD	-
Surface tension	Din 53364	mN/m	Plain side	40
			Acrilyc side	38
Specific weight	ASTM D 1505-68 C	g/cm3	-	
Grammage	Internal	g/m2	25,5	
Yield	Internal	m2/kg	39,21	
THERMAL DATA				
Lamination temperature	Internal	C°	100-140	
Storage	dry and clean place in 20 C° and 40% of relative humidity			

Appliacable to thermal lamination on cartons for cosmetic, perfumes, wine, etc.
Theoretical values (rounded of first decimal place)

All recommendations about our products are based on our recently knowledge and do not mean a guarantee. As the products are used
for different applications we recommend to check its suitability before using it.